



### Morbern has created the perfect Balance for interior seating.

The Balance Collection by Morbern™ is ideal for any interior seating application from Marine Interiors to Automotive Seating as well as Corporate, Hospitality and Residential environments.

Offering the best of both worlds, the Balance Collection provides the benefits of performance upholstery, withstanding up to 500,000 double rubs, while having the soft hand of luxury.

Balance by Morbern has the design flexibility to work in most interior applications. With four patterns and nearly 60 colors to choose from, ranging from subtle to dynamic and traditional to edgy, the Balance Collection is perfect for a wide variety of settings.

#### Recommended Applications

- Automotive Seating and Trim
- Conference Room Seating
- Executive Seating
- Foyer and Lounge Seating
- General Office Seating
- Home Office Seating
- Hotel/Motel Seating
- Marine Interior
- Residential Seating
- RV Seating and Trim
- Work Station Seating



### Specifications

Patterns	LEGACY	RHYTHM	LYNX	HERITAGE
<b>Contents</b>	100% Polyurethane with a brushed woven poly/cotton backing	100% Polyurethane with a knitted polyester blend backing	100% Polyurethane with a knitted polyester blend backing	100% Polyurethane with a knitted polyester blend backing
<b>Total Thickness</b>	36.8 mils	37 mils	37 mils	37 mils
<b>Skin Thickness</b>	2 mils	2 mils	2 mils	2 mils
<b>Roll Width</b>	54 in	54 in	54 in	54 in
<b>Roll Size</b>	30 yds	30 yds	30 yds	30 yds
<b>Weight</b>	17.4 oz/l yd.	18.5 oz/l yd.	18.5 oz/l yd.	18.5 oz/l yd.
<b>Cold Crack</b>	-40° F	-25° F	-25° F	-25° F
<b>Abrasion Resistance:</b> No significant wear using #8 cotton duck with the Wyzenbeek method	200,000 Double Rubs	500,000 Double Rubs	500,000 Double Rubs	500,000 Double Rubs
<b>Weathermeter Resistance:</b> ASTM G135-00a, Cycle 1	250 Hr.	120 Hr.	120 Hr.	120 Hr.
<b>Tensile Strength:</b> ASTM D751	•	•	•	•
<b>Single Tear Strength:</b> Fed. Std. 191A-5134	•	•	•	•
<b>Trapezoid Tear Strength:</b> ASTM D1117	•	•	•	•
<b>FMVSS-302</b>	•	•	•	•
<b>California Flammability Regulation (Bulletin 117, Sec. E)</b>	•	•	•	•
<b>BIFMA Class A</b>	•	•	•	•
<b>UFAC Class 1</b>	•	•	•	•

\* Flammability and all corresponding data refer to typical performance in the specific test indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

### Care and Cleaning Instructions

To prevent build up of dirt and contaminants, which may cause permanent staining, periodic cleaning is highly suggested. The frequency of cleaning is dependent upon the environmental conditions that material is subjected to.

#### For Normal Use:

Most stains can be easily cleaned using warm soapy water or commercially available non-abrasive detergent solutions like Formula 409® or Mr. Clean® and clear water rinses. Always test a cleaner in an inconspicuous area first. Moderate scrubbing with a medium bristle brush will help dislodge soiling materials from the depressions of embossed surfaces. Repeat as needed.



**Note:** This information is offered for your general guidance only. It is accurate to the best of our knowledge at the time of printing, but it is not intended to relieve the user from its responsibility to investigate and understand other pertinent sources of information and to comply with the laws and procedures applicable to the safe handling and use of this material.

